

JAPANESE INDUSTRIAL STANDARD

JIS E 5401-1:1998

Carbon steel tyres for railway rolling stock—Quality requirements

(This English erratum corresponds to the erratum to the Japanese version issued in September, 2016.)

October, 2016

ERRATUM

Page 4

(Table 1-1)

Error:

Steel grade symbol	Mechanical properties <sup>4)</sup>		
	<i>A</i> % min	<i>KU</i> J min <sup>8)</sup>	HB <sup>7)</sup>
C67GT-N	14	15	

Correct:

Steel grade symbol	Mechanical properties <sup>4)</sup>		
	<i>A</i> % min	<i>KU</i> J min <sup>8)</sup>	HB <sup>7)</sup>
C67GT-N	10	10	

Page 5

(Table 1-2)

Error:

Steel grade symbol			Mechanical properties
Type	Symbol	Abbreviation	Value of impact J min <sup>3)</sup>
Class 2	STY-N	N	15

Correct:

Steel grade symbol			Mechanical properties
Type	Symbol	Abbreviation	Value of impact J min <sup>3)</sup>
Class 2	STY-N	N	10

NOTE: The second edition of the English version published in and after October, 2016 will include the content of this erratum.