

ERRATA

Page 2

Replace Table 2 with the following.

Symbol of grade	Tensile strength N/mm <sup>2</sup>	Hardness HB
FC100	100 min.	201 max.
FC150	150 min.	212 max.
FC200	200 min.	223 max.
FC250	250 min.	241 max.
FC300	300 min.	262 max.
FC350	350 min.	277 max.

Page 4

9.3 (2)

**Error :** In the case where a product exceeds 2000 kg, one piece of product shall be considered to be one batch.

**Correct :** In the case where a product exceeds 200 kg, one piece of product shall be considered to be one batch.

Remarks: This erratum is for correcting the first edition of this Standard.

Japanese Standards Association