

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS B 1051 : 2014

(ISO 898-1 : 2013)

(JFRI/JSA)

**Mechanical properties of fasteners
made of carbon steel and alloy
steel—Bolts, screws and studs
with specified property classes—
Coarse thread and fine pitch thread**

ICS 21.060.10

Reference number : **JIS B 1051 : 2014 (E)**

B 1051 : 2014 (ISO 898-1 : 2013)

Date of Establishment: 1972-06-01

Date of Revision: 2014-09-22

Date of Public Notice in Official Gazette: 2014-09-22

Investigated by: Japanese Industrial Standards Committee
Standards Board

Technical Committee on Machine Elements

JIS B 1051:2014, First English edition published in 2015-02

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

AT

PROTECTED BY COPYRIGHT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references	2
3 Terms and definitions	5
4 Symbols and abbreviated terms	6
5 Designation system for property classes	8
6 Materials	8
7 Mechanical and physical properties	10
8 Applicability of test methods	16
8.1 General	16
8.2 Loadability of fasteners	16
8.3 Manufacturer's test/inspection	17
8.4 Supplier's test/inspection.....	17
8.5 Purchaser's test/inspection.....	17
8.6 Feasible tests for groups of fasteners and machined test pieces	17
9 Test methods	26
9.1 Tensile test under wedge loading of finished bolts and screws (excluding studs).....	26
9.2 Tensile test for finished bolts, screws and studs for determination of tensile strength, R_m	30
9.3 Tensile test for full-size bolts, screws and studs for determination of elongation after fracture, A_r , and stress at 0.004 $8d$ non-proportional elongation, R_{pf}	32
9.4 Tensile test for bolts and screws with reduced loadability due to head design	35
9.5 Tensile test for fasteners with waisted shank	36
9.6 Proof load test for finished bolts, screws and studs.....	38
9.7 Tensile test for machined test pieces	40
9.8 Head soundness test	43
9.9 Hardness test	44
9.10 Decarburization test.....	46
9.11 Carburization test	49
9.12 Retempering test	51
9.13 Torsional test	52
9.14 Impact test for machined test pieces.....	53

9.15	Surface discontinuity inspection	53
10	Marking	54
10.1	General	54
10.2	Manufacturer's identification mark	54
10.3	Marking and identification of fasteners with full loadability	54
10.4	Marking and identification of fasteners with reduced loadability	58
10.5	Marking of packages	59
Annex A (informative)	Relationship between tensile strength and elongation after fracture	60
Annex B (informative)	Influence of elevated temperatures on mechanical properties of fasteners	61
Annex C (informative)	Elongation after fracture for full-size fasteners, A_f	62

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by The Japan Research Institute for Screw Threads and Fasteners (JFRI)/Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law applicable to the case of revision by the provision of Article 14.

Consequently **JIS B 1051**:2000 is replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

Mechanical properties of fasteners made of carbon steel and alloy steel— Bolts, screws and studs with specified property classes—Coarse thread and fine pitch thread

Introduction

This Japanese Industrial Standard has been prepared based on the fifth edition of **ISO 898-1** published in 2013 without any modifications of the technical contents.

The portions with dotted underlines are the matters not given in the corresponding International Standard.

1 Scope

This Standard specifies mechanical and physical properties of bolts, screws and studs made of carbon steel and alloy steel when tested at an ambient temperature range of 10 °C to 35 °C. Fasteners (the term used when bolts, screws and studs are considered all together) that conform to the requirements of this Standard are evaluated at that ambient temperature range. They might not retain the specified mechanical and physical properties at elevated temperatures (see Annex B) and/or lower temperatures.

NOTE 1 Fasteners conforming to the requirements of this Standard are used in applications ranging from -50 °C to +150 °C. Users are advised to consult an experienced fastener metallurgist for temperatures outside the range of -50 °C to +150 °C and up to a maximum temperature of +300 °C when determining appropriate choices for a given application.

NOTE 2 Information for the selection and application of steels for use at lower and elevated temperatures is given, for example, in **EN 10269**, **ASTM F2281** and in **ASTM A320/A320M**.

Certain bolts and screws might not fulfil the tensile or torsional requirements of this Standard because the geometry of their heads reduces the shear area in the head compared to the stress area in the thread. These include bolts and screws having a low or countersunk head (see **8.2**).

This Standard is applicable to bolts, screws and studs

- made of carbon steel or alloy steel,
- having triangular **ISO** metric screw thread in accordance with **JIS B 0205-1**,
- with coarse pitch thread M1.6 to M39, and fine pitch thread M8×1 to M39×3,
- with diameter/pitch combinations in accordance with **JIS B 0205-2** and **JIS B 0205-3**, and
- having thread tolerances in accordance with **JIS B 0209-1**, **JIS B 0209-2** and **JIS B 0209-4**.