



JAPANESE  
INDUSTRIAL  
STANDARD

Translated and Published by  
Japanese Standards Association

---

JIS G 1228-3 : 2022

(JISF)

**Iron and steel — Determination of  
nitrogen — Part 3: Thermal  
conductimetric method after fusion in a  
current of inert gas**

JIS G 1228-3 : 2022 was revised under date of 21 August 2022.  
The revised items are included in Amendment 1.

---

ICS 77.080.01

Reference number : JIS G 1228-3 : 2022 (E)

PROTECTED BY COPYRIGHT

11 S

Date of Establishment: 2022-10-20

Date of Public Notice in Official Gazette: 2022-10-20

Developed by: The Japan Iron and Steel Federation

Investigated by: The Japan Iron and Steel Federation,  
Standardization Center

---

JIS G 1228-3 : 2022, First English edition published in 2024-02

Translated and published by: Japanese Standards Association  
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

---

In the event of any doubts arising as to the contents,  
the original JIS is to be the final authority.

© JSA 2024

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HN

## Contents

	Page
Introduction .....	1
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 General .....	2
5 Summary .....	3
6 Reagents .....	3
7 Apparatus and instruments .....	4
8 Weighing of sample .....	5
9 Procedure .....	5
9.1 Preparatory operation .....	5
9.2 Determination .....	5
10 Blank test .....	6
11 Preparation of calibration curve .....	7
11.1 General .....	7
11.2 Calibration curve with nitrogen standard solution .....	7
11.3 Calibration curve with steel and iron certified reference material .....	9
12 Correction of calibration curve .....	9
13 Calculation .....	10
13.1 Calibration curve with nitrogen standard solution .....	10
13.2 Calibration curve with steel and iron certified reference material .....	10
14 Precision .....	11
Annex JA (informative) Comparison table between JIS and corresponding International Standard .....	13

## Foreword

This Japanese Industrial Standard has been established by the Minister of Economy, Trade and Industry based on the provision of Article 14, paragraph (1) of the Industrial Standardization Act in response to a proposal for establishment of Japanese Industrial Standard with a draft being attached, submitted by The Japan Iron and Steel Federation (JISF), an accredited standards development organization. This Standard partially replaces **JIS G 1228** : 2006, which has been withdrawn.

This **JIS** document is protected by the Copyright Act.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, published patent application or utility model rights. The relevant Minister is not responsible for identifying any of such patent rights, published patent application or utility model rights.

**JIS G 1228** series consists of the following 3 parts under the general title *Iron and steel — Determination of nitrogen* :

*Part 1 : Amidosulfuric acid titrimetric method after ammonium distillation separation*

*Part 2 : Spectrophotometric methods after ammonium distillation separation*

*Part 3 : Thermal conductimetric method after fusion in a current of inert gas*

# Iron and steel-Determination of nitrogen-Part 3 : Thermal conductimetric method after fusion in a current of inert gas

## Introduction

This Japanese Industrial Standard has been prepared based on **ISO 10720** : 1997, Edition 1, with some modifications of the technical contents.

The vertical lines on both sides and dotted underlines indicate changes from the corresponding International Standard. A list of modifications with the explanations is given in Annex JA.

## 1 Scope

This Standard specifies the thermal conductimetric method after fusion in a current of inert gas, among methods for the determination of nitrogen in steel and iron.

The method is applicable to the determination of a nitrogen content (mass fraction) of 0.000 8 % or over up to and including 0.5 %.

NOTE 1 The determination range in **JIS G 1228** (all parts) is shown in Table 1.

**Table 1 Determination range in JIS G 1228 (all parts)**

Standard No.	Determination range [mass fraction (%)]
<b>JIS G 1228-1</b>	0.002 or over up to and incl. 0.5
<b>JIS G 1228-2</b>	0.000 5 or over up to and incl. 0.050
<b>JIS G 1228-3</b>	0.000 8 or over up to and incl. 0.5

NOTE 2 The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows.

ISO 10720 : 1997 *Steel and iron — Determination of nitrogen content — Thermal conductimetric method after fusion in a current of inert gas (MOD)*

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21-1**.

## 2 Normative references

Part or all of the provisions of the following standards, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.