

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS G 3444 : 2021

(JISF)

Carbon steel tubes for general structure

ICS 23.040.10 ; 77.140.10 ; 77.140.75

Reference number : JIS G 3444 : 2021 (E)

G 3444 : 2021

Date of Establishment: 1961-02-01

Date of Revision: 2021-02-22

Date of Public Notice in Official Gazette: 2021-02-22

Investigated by: Japanese Industrial Standards Committee

Standards Board for ISO area

Technical Committee on Metal and Inorganic Materials

JIS G 3444 : 2021, First English edition published in 2021-08

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2021

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HN

PROTECTED BY COPYRIGHT

Contents

		Page
1	Scope	1
2	Normative references	1
3	Symbol of grade	1
4	Manufacturing method	2
5	Chemical composition	2
6	Mechanical properties	3
6.1	Tensile strength and yield point or proof stress	3
6.2	Elongation	4
6.3	Flattening resistance	5
6.4	Bendability	5
7	Dimensions, unit mass and dimensional tolerances	6
7.1	Dimensions and unit mass	6
7.2	Dimensional tolerances	9
8	Appearance	11
9	Tests	12
9.1	Chemical analysis	12
9.2	Mechanical tests	12
10	Inspection and reinspection	16
10.1	Inspection	16
10.2	Reinspection	16
11	Marking	16
12	Report	17
Annex A (normative)	Type of coating and coating mass for tubes manufactured from coated steel sheet or coated steel strip	18

Foreword

This Japanese Industrial Standard has been revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee as the result of proposal for revision of Japanese Industrial Standard submitted by The Japan Iron and Steel Federation (JISF) with a draft being attached, based on the provision of Article 12, paragraph (1) of the Industrial Standardization Act applied mutatis mutandis pursuant to the provision of Article 16 of the said Act. This edition replaces the previous edition (**JIS G 3444 : 2016**), which has been technically revised.

However, **JIS G 3444 : 2016** may be applied in the **JIS** mark certification based on the relevant provisions of Article 30, paragraph (1), etc. of the Industrial Standardization Act until 21 February 2022.

This **JIS** document is protected by the Copyright Act.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, published patent application or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, published patent application or utility model rights.

Carbon steel tubes for general structure

1 Scope

This Japanese Industrial Standard specifies requirements for the carbon steel tubes (hereafter referred to as tubes), used for civil engineering and architecture such as steel towers, scaffoldings, footing piles, foundation piles, piles for landslide suppression.

NOTE The dimensional range covered by this Standard is generally outside diameter 21.7 mm to 1 016.0 mm. In application for foundation piles and piles for landslide suppression, however, this Standard is mainly applicable to tubes of outside diameter under 318.5 mm, and **JIS A 5525** applies mainly to welded steel tubes of outside diameter 318.5 mm or over.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

- JIS G 0320 *Standard test method for heat analysis of steel products*
- JIS G 0321 *Product analysis and its tolerance for wrought steel*
- JIS G 0404 *Steel and steel products — General technical delivery requirements*
- JIS G 0415 *Steel and steel products — Inspection documents*
- JIS G 3302 *Hot-dip zinc-coated steel sheet and strip*
- JIS G 3313 *Electrolytic zinc-coated steel sheet and strip*
- JIS G 3314 *Hot-dip aluminium-coated steel sheet and strip*
- JIS G 3317 *Hot-dip zinc-5 % aluminium alloy-coated steel sheet and strip*
- JIS G 3321 *Hot-dip 55 % aluminium-zinc alloy-coated steel sheet and strip*
- JIS G 3323 *Hot-dip zinc-aluminium-magnesium alloy-coated steel sheet and strip*
- JIS Z 2241 *Metallic materials — Tensile testing — Method of test at room temperature*
- JIS Z 3121 *Methods of tensile test for butt welded joints*
- JIS Z 8401 *Rounding of numbers*

3 Symbol of grade

The tubes are classified into 5 grades, and the symbol of grade shall be as given in Table 1.