

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS K 6252-1 : 2015

(JRMA/JSA)

**Rubber, vulcanized or
thermoplastic—Determination of
tear strength—Part 1: Trouser,
angle and crescent test pieces**

ICS 83.060

Reference number : **JIS K 6252-1 : 2015 (E)**

Date of Establishment: 2015-02-20

Date of Public Notice in Official Gazette: 2015-02-20

Investigated by: Japanese Industrial Standards Committee
Standards Board for ISO area
Technical Committee on Chemical Products and
Analytical Methods

JIS K 6252-1:2015, First English edition published in 2015-12

Translated and published by: Japanese Standards Association
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

AT

Contents

	Page
Introduction.....	1
1 Scope.....	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
4.1 General	2
4.2 Method A: Using a trouser test piece	3
4.3 Method B, procedure (a): Using an unnicked angle test piece	3
4.4 Method B, procedure (b): Using a nicked angle test piece	3
4.5 Method C: Using a crescent test piece	3
5 Apparatus	3
5.1 Dies for test pieces	3
5.2 Nick cutter.....	4
5.3 Testing machine.....	5
5.4 Grips	5
6 Calibration of test apparatus.....	6
7 Test piece	6
7.1 Preparation of sample.....	6
7.2 Conditioning of sample and cutting of test pieces	6
7.3 Grain of test piece	6
7.4 Cut or nick of test piece	7
8 Number of test pieces	7
9 Temperature of test.....	7
10 Test method.....	8
10.1 Measuring the thickness of the test piece	8
10.2 Procedure	8
11 Calculation.....	8
11A Precision.....	8
12 Test report	8
Annex A (informative) Precision	10
Annex B (normative) Calibration of test apparatus	12
Annex JA (informative) Comparison table between JIS and corresponding International Standard	14

Foreword

This translation has been made based on the original Japanese Industrial Standard established by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee according to the proposal for establishment of Japanese Industrial Standard submitted by The Japan Rubber Manufacturers Association (JRMA)/Japanese Standards Association (JSA) with the draft being attached, based on the provision of Article 12 Clause 1 of the Industrial Standardization Law. Consequently **JIS K 6252**:2007 has been withdrawn and partially replaced with this Standard.

This **JIS** document is protected by the Copyright Law.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, applications for a patent after opening to the public or utility model rights. The relevant Minister and the Japanese Industrial Standards Committee are not responsible for identifying any of such patent rights, applications for a patent after opening to the public or utility model rights.

JIS K 6252 series consists of the following 2 parts under the general title “*Rubber, vulcanized or thermoplastic—Determination of tear strength*”:

Part 1: Trouser, angle and crescent test pieces

Part 2: Small (Delft) test pieces

Rubber, vulcanized or thermoplastic— Determination of tear strength— Part 1: Trouser, angle and crescent test pieces

Introduction

This Japanese Industrial Standard has been prepared based on the third edition of **ISO 34-1** published in 2010 with some modifications of the technical contents.

The portions given sidelines or dotted underlines are the matters in which the contents of the corresponding International Standard have been modified. A list of modifications with the explanations is given in Annex JA.

1 Scope

This Standard specifies test methods for the determination of the tear strength of vulcanized or thermoplastic rubber.

This Standard applies to the following three test methods.

Method A Using a trouser test piece

Method B Using an angle test piece, with or without a nick of specified depth

Method C Using a crescent test piece with a nick

NOTE 1 Test method for the determination of the tear strength of Delft test pieces is specified in **JIS K 6252-2** (see Bibliography [1]).

NOTE 2 The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows.

ISO 34-1:2010 *Rubber, vulcanized or thermoplastic—Determination of tear strength—Part 1: Trouser, angle and crescent test pieces* (MOD)

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21-1**.

WARNING Persons using this Standard should be familiar with normal laboratory practice. This Standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this Standard to establish appropriate safety and health practices.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Standard. For standards with the year indication, only the editions of the indicated year shall be applied and the revisions (including amendments) made thereafter shall not be applied. For those without the indication of the year, the most recent edition (including amendments) shall be applied.