

JIS

JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS L 3201 : 2002

Wool press felts

ICS 59.080.30

Reference number : JIS L 3201 : 2002 (E)

L 3201 : 2002

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of Economy, Trade and Industry through deliberations at the Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law. Consequently **JIS L 3201 : 1997** is replaced with **JIS L 3201 : 2002**.

Date of Establishment: 1958-10-07

Date of Revision: 2002-03-20

Date of Public Notice in Official Gazette: 2002-03-20

Investigated by: Japanese Industrial Standards Committee
Standards Board
Technical Committee on Consumer Life
Products

JIS L 3201 : 2002, First English edition published in 2003-04

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

PROTECTED BY COPYRIGHT

Wool press felts

Introduction This Japanese Industrial Standard to which no International Standards correspond was developed in 1958 as the quality standard for wool press felts in Japan.

In the revision on this occasion, the numbers and titles of the standards which applied to this Standard as the normative references were changed with their revision and the form of presentation was also changed in accordance with **JIS Z 8301**.

1 Scope This Standard specifies wool press felts for industrial use in general⁽¹⁾ (hereafter referred to as “felts”).

Note ⁽¹⁾ The felts referred here do not contain those having passed the weaving process.

2 Normative references The following standards contain provisions which, through reference in this Standard, constitute provisions of this Standard. The most recent editions of the standards (including amendments) indicated below shall be applied.

JIS K 8161 *Dichloromethane*

JIS L 0105 *General principles of physical testing methods for textiles*

JIS L 1030-1 *Testing methods for quantitative analysis of fiber mixtures—Part 1 : Testing methods for fiber identification*

JIS L 1030-2 *Testing methods for quantitative analysis of fibre mixtures of textiles—Part 2 : Testing methods for quantitative analysis of fibre mixtures*

JIS R 3503 *Glass apparatus for chemical analysis*

JIS Z 8401 *Guide to the rounding of numbers*

JIS Z 8802 *Methods for determination of pH of aqueous solutions*

3 Classification Felts shall be classified as follows:

- a) R36W
- b) R33W
- c) R28W
- d) R25W1
- e) R25W2
- f) R19W
- g) R25M
- h) R23M
- i) R19M
- j) R17M