



JAPANESE
INDUSTRIAL
STANDARD

Translated and Published by
Japanese Standards Association

JIS M 8229 : 1997

Iron ores — Method for determination of lead content

ICS 73.060.10

Descriptors : determination of content, chemical analysis and testing, lead,
non-ferrous metals, iron ores, metalliferous minerals

Reference number : JIS M 8229 : 1997 (E)

Foreword

This translation has been made based on the original Japanese Industrial Standard revised by the Minister of International Trade and Industry through deliberations at Japanese Industrial Standards Committee in accordance with the Industrial Standardization Law. Consequently JIS M 8229:1983 is replaced with JIS M 8229:1997.

In this revision, the relevant provisions of ISO Standard are described, intending conformance with International Standard.

Date of Establishment: 1965-09-01

Date of Revision: 1997-08-20

Date of Public Notice in Official Gazette: 1997-08-20

Investigated by: Japanese Industrial Standards Committee
Divisional Council on Iron and Steel

JIS M 8229 :1997, First English edition published in 1998-09

Translated and published by: Japanese Standards Association
4-1-24, Akasaka, Minato-ku, Tokyo, 107-8440 JAPAN

In the event of any doubts arising as to the contents,
the original JIS is to be the final authority.

© JSA 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

Iron ores — Method for determination of lead content

Introduction This Standard is JIS prepared based on the provisions of lead of **ISO 8753**, *Iron ores – Determination of lead and/or zinc content – Flame atomic absorption spectrometric method* published in 1987, without modifying the technical content and the structure of the standard.

1 Scope This Japanese Industrial Standard specifies the methods for determination of lead content in iron ores.

2 Classification of determination method The method for determination of zinc content in iron ores shall be as follows.

Flame atomic absorption spectrometric method [identical with International standard (ISO 8753)] This method is applicable to a concentration range of 0.001 % (m/m) to 0.5 % (m/m) of lead, which is as described in Annex.