

# JIS

JAPANESE  
INDUSTRIAL  
STANDARD

Translated and Published by  
Japanese Standards Association

---

JIS Z 2248 : 2022

(JISF)

**Metallic materials — Bend test**

---

ICS 77.040.10

Reference number : JIS Z 2248 : 2022 (E)

PROTECTED BY COPYRIGHT

13 S

Z 2248 : 2022

Date of Establishment: 1952-10-23

Date of Revision: 2022-03-22

Date of Public Notice in Official Gazette: 2022-03-22

Developed by: The Japan Iron and Steel Federation

Investigated by: The Japan Iron and Steel Federation, Standardization  
Center

---

JIS Z 2248 : 2022, First English edition published in 2022-08

Translated and published by: Japanese Standards Association  
Mita MT Building, 3-13-12, Mita, Minato-ku, Tokyo, 108-0073 JAPAN

---

In the event of any doubts arising as to the contents,  
the original JIS is to be the final authority.

© JSA 2022

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

Printed in Japan

HN

PROTECTED BY COPYRIGHT

## Contents

	Page
Introduction .....	1
1 Scope .....	1
2 Normative reference .....	1
3 Term and definition .....	1
4 Symbols and designations .....	1
5 Principle of testing .....	2
6 Test equipment .....	2
6.1 General .....	2
6.2 Bending device with supports and former (pressing bend method) .....	5
6.3 Bending device with clamp (winding bend method) .....	6
6.4 Bending device with mandrel or mould (winding bend method) .....	6
6.5 Bending device with V-block and former (V-block method) .....	6
7 Test piece .....	6
7.1 General .....	6
7.2 Edges and side faces of rectangular test pieces .....	7
7.3 Shapes and dimensions of test pieces .....	7
7.4 Test pieces taken from forgings, castings and semi-finished products .....	9
7.5 Agreement on wide and thick test pieces .....	9
8 Test methods .....	9
8.1 Test temperature .....	9
8.2 Test procedure .....	9
9 Interpretation of results .....	11
10 Test report .....	12
Annex A (informative) Determination of the bend angle from the measurement of the displacement of the former .....	13
Annex B (informative) Bend test at plane strain conditions .....	14
Annex JA (informative) Comparison table between JIS and corresponding International Standard .....	18

## Foreword

This Japanese Industrial Standard has been revised by the Minister of Economy, Trade and Industry based on the provision of Article 14, paragraph (1) of the Industrial Standardization Act applied mutatis mutandis pursuant to the provision of Article 16 of the said Act in response to a proposal for revision of Japanese Industrial Standard with a draft being attached, submitted by The Japan Iron and Steel Federation (JISF), an accredited standards development organization. This edition replaces the previous edition (**JIS Z 2248** : 2014), which has been technically revised.

This **JIS** document is protected by the Copyright Act.

Attention is drawn to the possibility that some parts of this Standard may conflict with patent rights, published patent application or utility model rights. The relevant Minister is not responsible for identifying any of such patent rights, published patent application or utility model rights.

# Metallic materials — Bend test

## Introduction

This Japanese Industrial Standard has been prepared based on **ISO 7438** : 2020, Edition 4, with some modifications of the technical contents.

The vertical lines on both sides and dotted underlines indicate changes from the corresponding International Standard. A list of modifications with the explanations is given in Annex JA.

## 1 Scope

This Standard specifies the method of bend test for metallic materials <sup>1)</sup>.

Annex B shows the method of bend test at plane strain conditions by agreement between the purchaser and the supplier, for reference.

**NOTE** The International Standard corresponding to this Standard and the symbol of degree of correspondence are as follows.

ISO 7438 : 2020 *Metallic materials — Bend test* (MOD)

In addition, symbols which denote the degree of correspondence in the contents between the relevant International Standard and **JIS** are IDT (identical), MOD (modified), and NEQ (not equivalent) according to **ISO/IEC Guide 21-1**.

Note <sup>1)</sup> In ISO 7438, it is described as “a method for determining the ability of metallic materials to undergo plastic deformation in bending”.

## 2 Normative reference

Part or all of the provisions of the following standard, through reference in this text, constitute provisions of this Standard. The most recent edition of the standard (including amendments) indicated below shall be applied.

JIS G 0202.....*Glossary of terms used in iron and steel (Testing)*

## 3 Term and definition

For the purpose of this Standard, the following term and definition, and those given in **JIS G 0202** apply.

### 3.1

#### test force

force applied to test piece for the purpose of testing

## 4 Symbols and designations

The devices used in the bend test are as shown in Figure 1 to Figure 5, and the sym-